

ANTIK TINKTUR™ NEUTRAL

XS510T

Becker Acroma

DESCRIPTION

ANTIK TINKTUR NEUTRAL dry glaze is a dry glazing material for an antique look on solid colours and stains. This product can be tinted with Becker Acroma Arti Pigment Concentrates for tinting at up to 2 % maximum. Spray on, allow to dry, then remove the excess with a Scotchbrite pad or equivalent. This dry glaze is easy to apply, has excellent adhesion and dries quickly.

HIGHLIGHTS

- » **Dry Glaze**
- » **Dries Quickly**
- » **Easy to Apply**
- » **Use Arti Pigment Concentrates**
- » **Excellent Adhesion**
- » **Spray or Brush Application**

PRODUCT DATA:

| | | | |
|---------------------------|-----------------------|----------------------------|----------------------------------|
| Colour: | Wet: Milky Dry: Milky | VOC: | 773 g/l or 6.44 lbs/gal |
| Solids % by Vol.: | 3 % (Theoretical) | Lbs. VOC / Lbs. Solids: | 10.19 |
| Solids % by Wt.: | 9 % (Theoretical) | Lbs. VHAPs / Lbs. Solids: | 0.73 |
| Weight / Gal.: | 7.08 lb | Flash Point (PMCC): | 11° C / 52° F |
| Spec. Gravity: | 0.85 | Frost Sensitivity | No |
| Viscosity 23°C / 73°F: | #4 Ford: Thixotropic | Photo chemically Reactive: | Yes |
| Viscosity 23°C / 73°F: | DIN 4: Thixotropic | Shelf Life: | 1 year (at 15-25° C / 59°-77° F) |
| Theoretical Coverage: N/A | | | |

MIXING / APPLICATION:

Working Temp: >18° C, 65° F substrate, coating and air
Hardener: NA
Catalyzation: NA
Pot Life: 1 year (15-25°C / 59-77°F)
Mixing: Mix well before use.
Sealer: Can be used over Nitrocellulose and acid cured sealer and topcoats.
Reducer: Do not reduce.
Application: Spray
Surface Prep: Sand sealer coat before applying.
Use Directions: For interior use only. Mix thoroughly before application. Apply by dry spray, shade on until desired coverage is achieved, let dry then remove excess with a synthetic abrasive pad. Must be topcoated for protection.
App. Equip.: Conventional & HVLP Siphon or Gravity Feed and Pressure Pot Systems.
Tinting: Can be tinted with Becker Acroma Arti Pigment Concentrates to a maximum of 2%. Prior to application test a sample piece to assure proper colour.

DRYING TIMES TO SAND / STACK / CURE:

| Method | Drying Temp. | Drying Time (@ 60 % RH and thickness @ 1 mil dry) |
|----------------|----------------|---|
| Air Drying | 20° C / 68° F | 10-30 min. dry to sand |
| *Forced Drying | 70° C / 158° F | |

TESTING: Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

FOR INDUSTRIAL SHOP APPLICATION: Thoroughly review Material Safety Data Sheet (MSDS) for safety information and cautions prior to using this product. For Regulatory compliance data i.e. VOC, HAPS, etc., obtain an Environmental Data Sheet (EDS) prior to using the product. A MSDS and/or EDS is available from your local distributor or representative. Please direct any questions or comments to 1-800-524-5979.

NOTE: Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, The Sherwin-Williams Company cannot make any warranties as to the end result.