

Product Code:

423-2710	Flat Gloss
423-2720	Low Gloss
423-2735	Satin Gloss
423-2750	Semi-Gloss

VISCOSITY :	Z #2/40" at 77° F
FLASH POINT:	>140° F
DENSITY (lb/gal):	9.65
SOLID (% by weight):	42.3%
SOLID (% by volume):	32.5%
SHELF LIFE (months):	6

Product Description: Aquaset is a very durable white topcoat, formulated with a self-crosslinking polymer for maximum chemical resistance. Aquaset will give a smooth and hardwearing surface, resisting influence from alcohol, water, etc. Aquaset also has very good light stability based on the type of resin used.

Aquaset meets Kitchen Cabinet Manufacturer Association (KCMA) standards.

Uses: Aquaset is designed for interior applications such as kitchen cabinets, high build office furniture, residential furniture, molding, window and door frames, and other applications.

Environmental Data (as supplied):

VOC less exempt lb/gal:	<2.00
VOC lb/gal:	<0.86
VOC less exempt g/l:	<235
VOC g/l:	<105
VOC lb/lb Solid:	<0.25
VHAPs lb/lb Solid:	<0.02

See individual compliance sheets for specific data

Application data:

SUGGESTED USES:	Wood Finish
MIXING RATIO:	N/A
POT LIFE:	N/A
APPLICATION VISCOSITY:	Z #2/40"
REDUCER:	Use water as required. This product requires very little water to lower the viscosity.
RETARDER:	N/A
CLEAN-UP SOLVENT:	Use water when in liquid state, use water / Butyl Cellosolve (800-5742) when material is semi-dried
RECOMMENDED WET FILM:	4 - 5 wet mils



AkzoNobel

Directions for Use

Aquaset WB Pigmented TC
423-27XX

Surface Preparation: Substrate must be sanded using 120, 150 or 180 grit paper prior to coating. The recommended primer is Aquaprime 550-1600. Primer should be sanded with 280/320 grit paper prior to being coated. The Primer should be coated within four hours of being sanded for maximum adhesion. When recoating, the previous coat of Aquaset must be sanded and the next coat applied within four hours.

General Information: Mix material before use. Add water to reduce if required and mix thoroughly. Apply by spray at 4 - 5 mils wet.

Aquaset must be agitated thoroughly at all times to ensure product consistency. Contact with metal surfaces should be avoided.

Maximum film build of total coating system must not exceed 4 mils dry.

The completed coating system should be checked for required properties prior to start-up of production.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR THE START-UP OF PRODUCTION.

Drying Times:

	At 68° F	Forced Drying Schedule
Tack Free Time:	20 minutes	15 minutes @ room temperature
Dry to Sand:	4 hours	15 minutes @ 110° F
Dry to Stack:	24 hours	15 minutes @ 140° F

Note: Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64° F/18° C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc.
1431 Progress Ave
High Point, NC 27261
336-841-5111