

Product Code:

546-5006

VISCOSITY:	Z #2/25" at 77°F
FLASH POINT:	-4°F (-20°C)
DENSITY (lb/gal):	7.4
SOLID (% by weight):	27%
SOLID (% by volume):	20%
SHELF LIFE (months):	12

Product Description: Chemseal Amber is a ready to use, nitrocellulose lacquer sealer. It is a single pack, conventional lacquer sealer. Chemseal Amber (546-5006) dries rapidly, powders well, and seals the substrate preparing it for the appropriate topcoat.

Uses: Various interior wood applications.

Environmental Data (as supplied):

VOC less exempt lb/gal:	<5.00
VOC lb/gal:	<3.75
VOC less exempt g/l:	<600
VOC g/l:	<450
VOC lb/lb Solid:	<1.90
VHAPs lb/lb Solid:	<0.10

Application Data:

SUGGESTED USES:	Wood Sealer
MIXING RATIO:	N/A
POT LIFE:	N/A
APPLICATION VISCOSITY:	Z #2/20 – 27"
REDUCER:	803-1298
RETARDER:	800-5328
CLEAN-UP SOLVENT:	803-1298
RECOMMENDED WET FILM:	2 – 5 mils
COVERAGE:	257 sq. ft/gal at 1 mil dry and at 100% transfer efficiency. Coverage will vary depending on method of application or coating thickness.



AkzoNobel

Directions for Use

Surface Preparation: Substrate must be sanded using 120, 150 or 180 grit steared paper prior to staining or coating. Sealers should be sanded with 280/320 grit steared paper prior to being coated.

General information: Chemseal Amber is applied in two or more coats; however, the dry film build should not exceed 1 – 2 mils. The dry film build of the total system should not exceed 4 mils. Chemseal Amber should be thoroughly stirred and mixed with an appropriate amount of reducer.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION.

Drying Times:

	At 68°F	At 122°F
Tack Free Time:	10 – 15 mins.	Flash off before entering oven
Dry to Sand:	30 - 45 mins.	15 – 20 mins.
Dry to Stack:	1 - 2 hours	20 – 30 mins.

Note: Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc
1431 Progress Ave
High Point, NC 27261
336-841-5111