

Product Code:

825-3700 Neutral	825-3705 Medium Brown
825-3701 Burnt Umber	825-3706 Burnt Sienna
825-3702 Van Dyke	825-3707 White
825-3703 Black	825-3708 Chocolate
825-3704 Raw Sienna	

VISCOSITY:	~2000 CPS at 77°F
FLASH POINT:	53°F (12°C)
DENSITY (lb/gal):	8.6 – 9.0
SOLID (% by weight):	21 – 36%
SOLID (% by volume):	19 - 24%
SHELF LIFE (months):	12

Product Description: Promatch® Chemglaze 825-37XX is an all-purpose glaze for furniture and cabinets. It should be stirred well due to the heavy concentration of certain additives and tints. Application may be by hand or spray. Promatch® Chemglaze is reducible.

Uses: Promatch® Chemglaze is used for coloring of wood and is especially developed for furniture coating systems. When properly applied, it will enhance the natural beauty of the wood. Promatch® Chemglaze is used for indoor use and is normally applied over a washcoat.

Environmental Data (as supplied):

VOC less exempt lb/gal:	5.50 – 6.00
VOC lb/gal:	5.00 – 6.00
VOC less exempt g/l:	665 - 720
VOC g/l:	665 - 720
VOC lb/lb Solid:	1.75 – 2.26
VHAPs lb/lb Solid:	0.20 – 0.30

Application Data:

SUGGESTED USES:	Wood Finish
MIXING RATIO:	N/A
POT LIFE:	N/A
APPLICATION VISCOSITY:	N/A
REDUCER:	800-4310
RETARDER:	N/A
CLEAN-UP SOLVENT:	800-4310
RECOMMENDED WET FILM:	N/A



AkzoNobel

Directions for Use

Promatch® Glaze SB Stain
825-37XX

General Information: Prior to use, mix Promatch® Chemglaze carefully and reduce viscosity by adding approximately 50 – 100% reducer. Apply the reduced Chemglaze by spraying or with a rag. Allow two to three minutes air drying before wiping. Wipe clean and do not leave on any excess material that may interfere with optimum adhesion.

Promatch® Chemglaze must be thoroughly agitated to ensure product consistency.

Product must be thoroughly agitated before use.

After wiping, brush blending, highlighting and complete drying, it can be overcoated by a suitable system such as Plasticlear (421-40XX), Plastofix® Light (421-48XX), Danspeed® Elite (424-44XX), Opticlear 900 (431-XXXX), Chemlack (441-50XX) as well as the sealers associated with these systems.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION.

Wipe on using a clean dry rag or spray on. Leave 2 – 3 minutes and wipe off.

Air dry 30 – 45 minutes or air dry for 15 minutes at room temperature followed by at least 15 minutes at 158°F.

Note: The suggested drying times must be adhered to in order to ensure proper adhesion.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc.
1431 Progress Ave
High Point, NC 27260
336-841-5111