

# AUS0846

## Ultraguard™ Low Sheen Sealer/Topcoat

Date: August 31, 2017 (supersedes all previous revisions)



### GENERAL INFORMATION

Axalta's Ultraguard™ Conversion Varnish Sealer/Topcoat is a premium quality, post-catalyzed, alkyd-amino sealer/topcoat, formulated to offer exceptional durability and physical properties. As a sealer it dries fast, has excellent holdout, and sands easy. As a topcoat it provides a consistent dead flat appearance. It is supplied ready to spray (after catalyzation) and needs no further reduction. This product is designed for Professional use only. For wood substrates only.



### 1. PRODUCTS

- AUS0846



### 2. MIXING RATIO

- Stir thoroughly, do not shake.
- Catalyzation: 5% 399-5003 by volume



### 3. SHELF LIFE @ 77°F (25°C)

- 18 months as packaged



### 4. CLEAN UP

- Dispose of dirty solvent and cleaning rags in a safe and compliant manner. Solvent or lacquer soaked rags should be stored in water-filled, closed containers prior to disposal.



### 5. ADDITIVES

- If required – use 390-9303-00 lacquer retarder to slow down evaporation rate of coating



### 6. SURFACE PREPARATION

- Surface must be clean and dust free with a moisture content of 6-8% prior to finishing. Remove all dust, dirt, wax and wood marks. Proper sanding and preparation of the wood is critical to achieving consistent results.
- On new wood, finish sand surface with 150-180 grit sandpaper
- On previously finished wood, remove all old paint or varnish and follow new wood procedure.



### 7. COMPANION PRODUCTS

- 379-7900 ULTRAGUARD™, 371-3115 SUPERSEAL™
- Graintone Plus™ stain system



### 8. TECH NOTES

- No thinning is recommended.



### 9. SUBSTRATES

- Commonly used furniture and cabinetry woods
- MDF/HDF

**NOTE:** Not to be used on exterior applications



### 10. APPLICATION

- See application notes for detailed instructions.



### 11. FLASH / DRY TIMES

AIR DRY @ 77°F (25°C)

|                     |                 |
|---------------------|-----------------|
| Dry to touch        | 15-20 Minutes   |
| Flash between coats | 35 - 45 Minutes |
| To Stack            | 12 - 16 Hours   |

### 12. FORCE DRY



|           |                    |
|-----------|--------------------|
| Flash     | 8 - 10 Minutes     |
| Bake      | 15 Minutes @ 140°F |
| Cool Down | 10 Minutes ambient |
| Stack     | After cool down    |



### 13. GUN SET UP



|                      |                     |
|----------------------|---------------------|
| Gravity Feed         | 1.4 mm - 1.8 mm     |
| Siphon Feed          | 1.4 mm - 1.8 mms    |
| Airless              | 10 - 15 thousandths |
| Air-Assisted Airless | 11 - 15 thousandths |

### AIR PRESSURES

|  |                         |
|--|-------------------------|
| Gravity Feed   | 30-35 psi (2.0-2.4 bar) |
| Siphon Feed  | 35-40 psi (2.4-2.8 bar) |
| Air-Assisted Airless                                 | 10-20 psi (0.7-1.4 bar) |
| See spray gun manufacturer data for more information |                         |



### 14. PHYSICAL DATA

|   |                           |
|---|---------------------------|
| Viscosity                                       | 19-23" @77F #2 EZ ZAHN    |
| Weight Solids %                                 | 31.28%                    |
| Volume Solids %                                 | 23.48%                    |
| Actual VOC                                      | 3.83 lbs/gal of Product   |
| VOC Ratio (lb.voc/lb.solids)                    | 1.70 (lb VOC/lb solid)    |
| Regulatory VOC (less water and exempt solvents) | 590 g/l                   |
| Weight Per Gallon                               | 7.69 lbs/gal              |
| Flash Point                                     | 0°F Closed Cup            |
| Theoretical Coverage                            | 376.62 ft/gal @ 1 mil dry |
| VHAP (lb.HAP/lb.solids)                         | .30 lb VHAP/lb solid      |
| Photochemically Reactive                        | No                        |
| Coating Category                                | Clear                     |



## Application Notes:

### General:

Always pre-test the system on your substrate to verify suitability of the application. If staining, use an approved Axalta Stain and let dry per the directions on the Technical Data Sheet for the stain you choose. Choose the appropriate sheen from the series and agitate well before applying. While under agitation, catalyze the conversion varnish with 5% 399-5003 by volume and let mix for 5-10 minutes or until the catalyst is thoroughly incorporated. Stir thoroughly before use and occasionally during use. Apply by spray only, using Conventional Air, HVLP, Airless, or Air Assisted Airless equipment. Apply at a rate of 3-4 wet mils per coat. Sand between coats with 240-320 grit, no fill type sandpaper. Remove sanding dust before applying the next coat. This finish must be sanded between coats for proper adhesion. **DO NOT APPLY more than three coats at 3-4 wet mils per coat when used as a self seal system. Maximum film thickness of the total coating system MUST NOT EXCEED 4 dry mils.**

### Drying Time:

Dry to touch: 15-20 minutes

Dry to sand and recoat: 35-45 minutes (depending on ambient conditions).

Do not apply if the material or substrate temperature is below 55°F.

This product is best applied when surface and air temperatures are between 55°-90° F (~12-32°C) and when relative humidity is below 50% during application and drying time.

### Potlife:

12-24 hrs using 399-5003 catalyst (Temperature and humidity can affect potlife, always measure catalyst accurately)

### Clean Up:

Use lacquer thinner to clean equipment. Refer to your local regulations for compliance requirements for cleaning thinners, or use recommended Axalta Lacquer Thinner. Dispose of dirty solvent and cleaning rags in a safe and compliant manner. Solvent or lacquer soaked rags should be stored in water-filled, closed containers prior to disposal

### Precautions:

These products are recommended for professional application and are designed for interior use only. Always pre-test the system on your substrate and under your line conditions to verify suitability to the application and to avoid potential need for costly refinishing. Axalta Industrial Wood Coatings are designed to protect and enhance the natural beauty of wood, but cannot eliminate natural discoloration or deterioration of wood as it ages.

### Additional notes:

Do not mix with other finishing systems or deviate from these finishing recommendations. Axalta will not be held liable for finish failures resulting from the mixing of products or deviations from finishing recommendations.

### Storage:

Store in a cool, dry place. **DO NOT FREEZE!** Product should be stored in temperatures between 50°-110°F. Close all containers after use. Do not store near heat or sparks. Spills should be cleaned up with non-sparking tools. [See the product SDS for complete safety information.](#)

### Warning:

Always pre-test the system on your substrate and under your line conditions to verify suitability to the application and avoid potential need for costly refinishing. All dry times listed are as tested under ideal indoor environmental conditions of 78°F (26°C) with relative humidity not exceeding 50%. These products are recommended for use under temperature conditions of 60-100°F (16-38°C) and when relative humidity is below 50% during application and drying time. Low temperatures, poor air circulation or high humidity will extend dry times. **Axalta strongly recommends against use of these products if temperatures of air, material, or surface to be coated are below 60°F (16°C) or below the dew point. Abnormal conditions of temperature or humidity may adversely affect product performance.** Please contact your authorized Axalta Industrial Wood Coatings distributor for additional product use recommendations and finishing guidance.