

TECHNICAL	\mathbf{D}_{I}	ΑT	Α
-----------	------------------	----	---

PRODUCT: LFR52x

DEFINITION: WHITE ACRYLIC TOP-COAT

CATALYST: LCB057 10%

DILUTING AGENT: LZD091

MAIN FIELDS OF USE:

Furntiture, various objects.

PROPERTIES:

Very good filling, superficial hardness, scratch resistance, and elasticity. Good resistance to yellowing and drying rapidity.

CHEMICAL-PHYSICAL PROPERTIES:

SPECIFIC WEIGHT: 1.200 ± 0.05

DRY RESIDUE : $47\% \pm 2$

VISCOSITY DIN 8: $35" \pm 2$

DRY AT ROOM dust free: 15 mins. TEMPERATURE: dry to touch: 40 mins.

thoroughly dry: 12 hours.

TIME INTERVAL BETWEEN

COATS (SANDING)

Min – max 4-12 hours

GLOSS METER MATT READING: LFR520 75 ± 3

LFR521 60 / 65 LFR522 50 ± 3 LFR523 35 / 40 LFR524 25 ± 3 LFR525 10 / 15

LFR526 5 ± 2



APPLICATION: QUANTITIES:	AIRLESS SPRAY	AIRMIX SPRAY
1 st coat g/sq.mt.	120-150	120-150
2 nd coat g/sq.mt	120-150	120-150
DILUTION	10-20%	10-20%

T.D. LFR52x October 2011 1°

IMPORTANT: The information contained in this technical data sheet is based on the average results obtained in our laboratories and is the best experience we have gained with the most rigorous, thorough tests and checks possible.

However, as every panel or support, even of the same type, may be different to every other one in terms of the characteristics that influence the outcome of painting operations considerably and as the environment, mixtures and the equipment used also contribute to the final results. The final result is thus the user's exclusive responsability he The information given herein is based on a temperature of 20° at 70% relative humidity.