

TECHNICAL DATA

PRODUCT CODE	LCW xxx (series)
DESCRIPTION	ISOCYANIC HARDENERS FOR WATER BASED PRODUCTS

MAIN FIELD OF USE:

Second component in reaction for polyurethane and acrylic water-based products.

CHEMICAL-PHYSICAL PROPERTIES:

They are expressed all average values calculated at 20°C / 68°F.

Code	Vx sec DIN Ø 4	S.C. %	S.C. Vol	S.W. g/l	S.W. lb/USgal	COV %	COV g/l	COV lb/USgal
LCW013	60"	80	76.74	1.120	9.353	20	232	1.94
Hardener for water-based products, interior and exterior								
LCW015	20"	73	72.22	1.070	8.935	27	298	2.49
Hardener for water-based products, interior and exterior								

REMARK:

The product, stored in the original cans well closed, preferably at a temperature between 5° and 30°C, has a shelf life of 12 months.

Once opened, use the remaining as soon as possible, by closing cap tightly each time: the product reacts with air humidity.

TDs LCW xxx (series) – 2017, October – revision NA01

IMPORTANT: The information contained in this technical data sheet are based on the average results obtained in our laboratories and is the best experience we have acquired in the most rigorous manner, thorough tests and checks.

Nuova S.I.V.A.M. guarantees the consistency of the chemical/physical characteristics of its products within the tolerances indicated above.

The final result is the full responsibility of the user who, before using the product, must check that it meets his requirements in terms of safety, application equipment, support material to paint, and environmental conditions.

The information given herein is based on a temperature of 20°C/68°F and 70% of relative humidity.

Nuova S.I.V.A.M. technical and commercial network is at your complete disposal to deal with any questions regarding how to correctly apply and use our products.

NUOVA SIVAM S.p.A. • v. Monviso, 10 • 20010 BAREGGIO (MI) • tel. 02/903041 • fax. 02/9014289 • <http://www.sivam.it> • e-mail: info@sivam.it