

## Excel S

### Technical Specifications

Properties	Typical Value*				ANSI A208.2-2016 (Grade 130)	
	< 9.53 mm (< 3/8")		9.53-12.7 mm (3/8"-1/2")		Metric	Imperial
	Metric	Imperial	Metric	Imperial		
Internal Bond	0.94 N/mm <sup>2</sup>	136 psi	0.70 N/mm <sup>2</sup>	102 psi	0.54 N/mm <sup>2</sup>	78 psi
MOR	29.4 N/mm <sup>2</sup>	4,260 psi	24.8 N/mm <sup>2</sup>	3,600 psi	21.6 N/mm <sup>2</sup>	3,130 psi
MOE	3,850 N/mm <sup>2</sup>	558,400 psi	3,440 N/mm <sup>2</sup>	499,000 psi	2,160 N/mm <sup>2</sup>	313,000 psi
Moisture Content	4-6%		4-6%		≤ 9%	

## Excel

### Technical Specifications

Properties	Typical Value*				ANSI A208.2-2016 (Grade 130)	
	15.88-19.05 mm (5/8"-3/4")		≥ 22.23 mm (≥ 7/8")		Metric	Imperial
	Metric	Imperial	Metric	Imperial		
Internal Bond	0.75 N/mm <sup>2</sup>	109 psi	0.62 N/mm <sup>2</sup>	90 psi	0.54 N/mm <sup>2</sup>	78 psi
MOR	24.3 N/mm <sup>2</sup>	3,525 psi	22.1 N/mm <sup>2</sup>	3,200 psi	21.6 N/mm <sup>2</sup>	3,130 psi
MOE	3,350 N/mm <sup>2</sup>	486,000 psi	3,125 N/mm <sup>2</sup>	453,000 psi	2,160 N/mm <sup>2</sup>	313,000 psi
Screw Holding:						
Face (≥ 3/8")	1,140 N	256 lb	1,080 N	243 lb	988 N	222 lb
Edge (≥ 5/8")	1,095 N	246 lb	965 N	217 lb	787 N	177 lb
Moisture Content	4-6%		4-6%		≤ 9%	

Thickness Tolerance:	Metric	Imperial
from specified thickness	± 0.125 mm	± 0.005 in
from panel average	± 0.125 mm	± 0.005 in
Length/Width	± 2.0 mm	± 0.080 in
Linear Expansion	≤ 0,33%	

All-purpose. Perfect for industrial applications, such as lamination and painting. Broad range of thicknesses available. Excel S upon availability only. For mouldings and other specific applications.

Thicknesses available: 1/4" to 1 1/8". Other thicknesses available on request, subject to minimum order.

Uniboard MDF meets the requirements of ANSI A208.2-2016/Grade 130, ECC 4-11, CARB ATCM 93120 and is available as FSC® certified

Uniboard MDF meets CARB Phase 2 standards

\* Typical values measured at the Mont-Laurier plant

Although the information in this document is presented in good faith and believed to be correct, Uniboard makes no representations or warranties as to the completeness or accuracy of the information. Uniboard shall have no liability for any errors or omissions contained therein or for any consequences of same.