

RICHELIEU HARDWARE LTD.

7900 Henri-Bourassa Ouest
St-Laurent, Quebec-QC, H4S 1V4 (CANADA)
☎ +1 450 664 0163 www.richelieu.com
E-mail: info@richelieu.com

White primer post-cat

Reference: **BE1003T**

Product description

Two-component white post-catalysed primer, high solids, fast drying, easy sanding.

Components

BZ1008T Catalyst at 10%.
DN2000M Reducer, if necessary 0% - 10%

Do not use other thinners and reducers than DN2000M.

Physical-chemical characteristics

Density: 1.200 g/cm³ ±0.010 at 20°C
Solid contents: 60%
Viscosity 130" ± 5 Ford 4 at 20°C
Mixture viscosity: 50" ± 2 Ford 4 at 20°C

Application systems

Application method is by spraying-gun, recommended coat thickness 120 to 150 gr/m².
Pot life: 8 hours

Drying system

Air drying and hot air drying which it can be accelerated with temperatures up to 30-40 °C. Easy sanding and high build.

Usage field

White primer for lacquering processes. Application on MDF, chipboard and veneers.

Storing and packaging.

Product must be stored away from electrical and heat sources. Don't smoke in the storage area. To avoid product leaking, once opened one package it will have to be carefully closed again and kept always in vertical position.

- *Maximum storing-time:* 12 months in original packaging,
- *Available packages:* 20 litre drums.

Remarks.

Shake well the product before use and make a first application test if the product was kept in stock for a long time after production.