



Technical Data Sheet

Product	KMT10x ColorSeries									
Description	Pigmented pastes for solvent-based tinting system									
Code/Color	CODE					COLOR				
	KMT10					White				
	KMT20					Vivid yellow				
	KMT21					Lemon yellow				
	KMT22					Gold yellow				
	KMT23					Oxide yellow				
	KMT26					Concentrated yellow				
	KMT31					Orange				
	KMT40					Green				
	KMT50A					Vivid red				
	KMT51					Wisteria red				
	KMT53					Oxide red				
	KMT54					Concentrated red				
	KMT60					Bordeaux				
	KMT70					Violet				
	KMT80					Blue				
	KMT90					Black				
Chemical-physical Properties										
CODE	Density (Kg/l)				Density (lb/US gal)			Solid content %		
KMT10	1,877	±	0,030		15,7	±	0,3		74,0	± 2
KMT20	1,020	±	0,030		8,5	±	0,3		48,0	± 2
KMT21	1,565	±	0,030		13,1	±	0,3		68,0	± 2
KMT22	1,081	±	0,030		9,0	±	0,3		49,0	± 2
KMT23	1,550	±	0,030		12,9	±	0,3		54,0	± 2
KMT26	1,035	±	0,030		8,6	±	0,3		48,0	± 2
KMT31	1,040	±	0,030		8,7	±	0,3		43,0	± 2
KMT40	1,074	±	0,030		9,0	±	0,3		46,0	± 2
KMT50A	1,028	±	0,030		8,6	±	0,3		39,0	± 2
KMT51	1,010	±	0,030		8,4	±	0,3		35,0	± 2
KMT53	1,720	±	0,030		14,4	±	0,3		39,0	± 2
KMT54	1,081	±	0,030		9,0	±	0,3		56,0	± 2
KMT60	1,056	±	0,030		8,8	±	0,3		54,0	± 2
KMT70	1,038	±	0,030		8,7	±	0,3		38,0	± 2
KMT80	1,060	±	0,030		8,8	±	0,3		32,0	± 2
KMT90	1,050	±	0,030		8,8	±	0,3		44,0	± 2



USAGE INDICATIONS	
Mechanically shake every single paste before use. It is advisable to add pastes under mechanical mixing. Quantities must be weighted with high precision balances.	
Shelf life	18 months after production

WARNINGS

In a coating process with professional products:

- besides the product quality, the final result also depends on numerous other variables, such as environmental conditions; homogeneity in the quality of the support; the constancy of the application cycle; the plants performance; the proper use of the product, etc.
- in the process of industrial coating a certain waste of product is to be considered normal and therefore not attributable to product quality
- The final colour is influenced by the quality and preparation of the support and the conditions of application, for this reason it is essential to check in advance the result in terms of final use

Our Company cannot ensure the control of the coating process carried out by the user. We cannot, therefore, take on any responsibility for the final result achieved through the use of our products. On the other hand, we guarantee the consistency of the chemical and physical characteristics of the product indicated in the relevant Technical Data Sheet, pledging to replace it if it does not correspond to the declared features. Data on the chemical and physical characteristics of the product are recorded at 20°C / 68°F and 70% R.U.

For best results, the optimum conditions of application are:

- Ambient temperature between 18 and 22°C (64 - 72 °F)
- ambient relative humidity between 65 and 70%
- support humidity between 8 and 14%

The conditions to be observed scrupulously are:

- A solvent-based product should be stored indoors at temperatures not below 0 °C / 32°F or above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- Always shake the products well before use
- Before use, always shake well the product mixed with any other components such as catalysts, accelerators, thinners
- The application must not take place at a temperature lower than 15 °C / 59°F or above 30°C / 86°F
- The drying should not take place at a temperature below 15 °C / 59°F
- The ambient relative humidity during drying should be between 50% and 70%
- To decant paints, exclusively use containers made of suitable material, such as polyethylene and stainless steel
- After use, we recommend that you always close the can carefully

The end result of the coating cycle is the sole responsibility of the users, who must make sure that the product matches their needs and that environmental conditions, application or media specifications do not require substantial changes of use

It is the user's responsibility:

- Adhere to the conditions indicated above
- comply with the rules of hygiene and safety during product application, according to the descriptions given in the safety data sheets
- for solvent-based products spark-proof equipment should be used
- It is forbidden to smoke while using the product

At the bottom of each sheet there is a date of validity

The Company invites you to check with their staff that the product data sheet in your possession is the most updated, since the characteristics of the products are subject to adjustments over time

For more information, please contact (see below):

Issue date: 01-2022

Rev.: 5