



## Clear sealer post-cat

### **RICHELIEU HARDWARE LTD.**

7900 Henri-Bourassa Ouest  
St-Laurent, Quebec-QC, H4S 1V4 (CANADA)  
☎ +1 450 664 0163 www.richelieu.com  
E-mail: info@richelieu.com

Reference: **BK9001T**

### **Product description**

Two-component clear sealer, high solids, fast drying, easy sanding.

### **Components**

BZ1008T      Catalyst at 10%.  
DN2000M      Reducer, if necessary 0% - 10%

*Do not use other thinners and reducers than DN2000M.*

### **Physical-chemical characteristics**

Density:	0.960 g/cm <sup>3</sup> ±0.010 at 20°C
Solid (% by weight):	42%
Viscosity	38" ± 3 Ford 4 at 20°C
Mixture viscosity:	28" ± 3 Ford 4 at 20°C

### **Application systems**

Application method is by spraying-gun, recommended coat thickness 90 to 150 gr/m<sup>2</sup>.  
Pot life: 8 hours

### **Drying system**

Air drying and hot air drying which it can be accelerated with temperatures up to 30-40 °C. Easy sanding and high build.

### **Usage field**

Varnish for furniture in general. Application on sanded solid wood and on veneer substrates.

### **Storing and packaging.**

Product must be stored away from electrical and heat sources. Don't smoke in the storage area. To avoid product leaking, once opened one package it will have to be carefully closed again and kept always in vertical position.

- *Maximum storing-time:*                      18 months in original packaging,
- *Available packages:*                        20 litre drums.

### **Remarks.**

Shake well the product before use and make a first application test if the product was kept in stock for a long time after production.