



RICHELIEU HARDWARE LTD.

7900 Henri-Bourassa Ouest St-Laurent, Quebec-QC, H4S 1V4 (CANADA) ☎ +1 450 664 0163 www.richelieu.com E-mail: info@richelieu.com

Clear post-cat 35°

Reference: **BN9015T**

Product description

Two-component multilayer clear topcoat, high solids, fast drying, silky touch.

Components

DN2000M Reducer, if necessary 0% - 10%

BZ1008T Catalyst at 10%.

Do not use other thinners and reducers than DN2000M.

Physical-chemical characteristics

Density: $0.970 \text{ g/cm}^3 \pm 0.010 \text{ at } 20^{\circ}\text{C}$

Solid (% by weight): 48 %

Viscosity 30" ± 3 Ford 4 at 20°C Mixture viscosity: 22" ± 3 Ford 4 at 20°C

Gloss: $35^{\circ} \pm 3$

Application systems

Application method is by spraying-gun or curtain-coater, with a recommended coat thickness 90 to 150 gr/m². Pot life: 8 hours

Drying system

Air drying and hot air drying which it can be accelerated with temperatures up to 30-40 °C.

Usage field

Varnish for furniture in general. Application on sanded primers, or on sanded veneers when used as multilayer coating.

Storing and packaging.

Product must be stored away from electrical and heat sources. Don't smoke in the storage area. To avoid product leaking, once opened one package it will have to be carefully closed again and kept always in vertical position.

Maximum storing-time: 18 months in original packaging,

Available packages: 20 litre drums.

Remarks.

Shake well the product before use and make a first application test if the product was kept in stock for a long time after production.

Date: 21.02.24 1of 1