

**RICHELIEU HARDWARE LTD.**

7900 Henri-Bourassa Ouest  
St-Laurent, Quebec-QC, H4S 1V4 (CANADA)  
☎ +1 450 664 0163 www.richelieu.com  
E-mail: info@richelieu.com

**White pre-cat 35°**Reference: **LM1005T****Product description**

White pre-catalysed topcoat, high solids, fast drying, good hiding power and silky touch.

**Components**

Reducer: DN2000M 10% - 20%

*Do not use other thinners and reducers than DN2000M.*

**Physical-chemical characteristics**

Density:	1.080 g/cm <sup>3</sup> ± 0.010 at 20°C
Solid (% by weight):	40 %
Viscosity	33 " ± 3 Ford 4 at 20°C
Gloss:	25° ± 5, 60° angle

**Application systems**

Spraying application. aerographic spraying-gun, recommended coat thickness 90 to 150 gr/m<sup>2</sup>. Dilute up to maximum 17-18 sec Ford 4.

**Drying system**

Drying of this product is very fast, heart drying in 60 min, but it can be accelerated with temperatures up to 30-40 °C.

**Usage field**

All kind of furniture in general, it can be applied on any kind of primer.

**Storing and packaging.**

Product must be stored away from electrical and heat sources. Don't smoke in the storage area. To avoid product leaking, once opened one package it will have to be carefully closed again and kept always in vertical position.

- *Maximum storing-time:* 18 months in original packaging,
- *Available packages:* 20 litres.

**Remarks.**

It must be prepared for use with the recommended reducer. However, if the room temperature is higher than 30°C it is convenient to use the retarder DU5023L. It is also recommended to use the retarder if the relative humidity is higher than 80-90%.